

HANAREY CSE9718-C Product Data Sheet

Nov 2023

Hanarey CSE9718-C is a one-component light and moisture-curable conformal coating designed to protect electric circuits against extreme environments. It has excellent moisture resistance and chemical resistance ability. Coating in shadowed areas cures over time with ambient moisture. The material cures upon exposure to light and is suitable for various kinds of spraying processes. Its ability to UV cure tack free in seconds enables faster processing, greater output, and lower processing costs. This product is certified to UL94-V0 standard and is in full compliance with RoHS 2.0 directive 2015/863/EU.

UNCURED PROPERTIES *

Property	Value	Test Method
Chemical Class	Acrylated Urethane	N/A
Appearance	Light Amber Transparent Liquid	N/A
Density, g/ml	1.08	ASTM D1875
Viscosity, cP	250~450	HSTM 751 [‡]
Shelf Life from Date of Manufacture	270 days	N/A

CURED MECHANICAL PROPERTIES *

Property	Value	Test Method
Hardness	D40~D70 ^Ω	ASTM D2240
	D75	ASTM D2240
Tensile at Break, MPa	13.57	ASTM D638
Elongation at Break, %	3.87	ASTM D638
Modulus of Elasticity, MPa	64	ASTM D638
CTE _{α1} , μm/m/°C	106	ASTM E831
CTE _{α2} , μm/m/°C	230	ASTM E831

* Not Specifications
 N/A Not Applicable
 ¥ Measured after UV cure followed by 10 days at 25°C/75% RH
 Ω Measured after UV cure only
 # Cured by Dymax 5000-EC (all spectrum), 120 mW/cm² intensity, 30 s
 ‡ HSTM refers to Hanarey Standard Test Method

OTHER CURED PROPERTIES *

Property	Value	Test Method
Boiling Water Absorption, % (2 h)	0.71	ASTM D570
Water Absorption, % (25°C, 24 h)	0.17	ASTM D570
Linear Shrinkage, %	2.15	ASTM D2566
Glass Transition Tg, °C	52	ASTM D5418

ELECTRICAL PROPERTIES *

Property	Value	Test Method
Dielectric Constant (1 MHz)	2.79	ASTM D150
Dissipation (1 MHz)	0.0234	ASTM D150
Dielectric Breakdown Voltage, kV/mm	59	HSTM D149 [‡]
Surface Resistivity, ohm	1.2*10 ¹⁴	ASTM D257
Volume Resistivity, ohm-cm	8.5*10 ¹⁴	ASTM D257

ADHESION *¥

Substrate	Shear Strength/ Cross-Cut
PC / PCB	22.32 MPa [#]
PCB	5B

TRANSPORTATION, STORAGE, AND SHELF LIFE

Do not crush and throw to avoid leakage during transportation. It is verified that the product is exposure to ambient temperature for a short time during transportation will not affect its performance. Store the material in a low-humidity, cool, and dark place when not in use. This product may polymerize upon prolonged exposure to ambient and artificial light as well as moisture. This material shelf life is noted on page 1 of this document when stored between 10°C (50°F) and 32°C (90°F) in the original, unopened container.


CLEAN UP

Uncured Hanarey materials may be removed from dispensing components and parts with non-alcoholic solvents. Cured material will be impervious to many solvents and difficult to remove. Cleanup of cured material may require mechanical methods such as ultrasonic bath, water, jet, vacuum tweezers, air knife, and/or warming to aid in the removal.

CURING GUIDELINES

First Step: light cure

The graph below shows the increase in depth of cure as a function of exposure time at Dymax 5000-EC 200 mW/cm². These depths are only due to light cure.



Second Step: > 7 days moisture cure

Full cure is best determined empirically by curing at different times and intensities and measuring the corresponding change in cured properties such as tackiness, adhesion, hardness, etc. Full cure is defined as the point at which more energy exposure no longer improves cured properties. Higher intensities or longer cures (up to 5x) generally will not degrade Hanarey light-curable adhesives.

Hanarey recommends that customers employ a safety factor by curing longer and/or at higher intensities than required for a full cure. Although Hanarey Application Engineering can provide technical support and assist with process development, each customer ultimately must determine and qualify the appropriate curing parameters required for their unique application.

GENERAL INFORMATION

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from the skin with soap and water. Never use organic solvents to remove material from the skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Hanarey performed under laboratory conditions as they existed at that time and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Hanarey does not guarantee that this product's properties are suitable for the user's intended purpose. The contents of this document are subject to change. Unless specifically agreed to in writing, Hanarey shall have no obligation to notify the user about any change to its content.

Data Collected: Nov 2023

Date of Revision: 16 Nov 2023